



Vasavibala Resins (P) Ltd.

POLYMER DIVISION
Manufacturers of Unsaturated Polyester Resins

TECHNICAL BROCHURE – UNSATURATED POLYESTER RESINS

GRADE : VBR 2305PA – Pre Accelerated Ortho Lamination Hi Spread Resin

VBR 2305PA is a medium reactive pre accelerated orthophthalic based laminating resin designed for the production of general-purpose products. This resin shows good wet out and rapid trim times in open mould process. This resin is suitable for use in spray-up and hand lay-up applications. It resists impact and thermal cracking.

PROPERTIES OF LIQUID RESIN

Appearance	Pale pinkish clear liquid
Viscosity at 25° C, cP (Brookfield Viscometer LV DV II + Pro Spindle 63, rpm 100)	300 – 400
Specific gravity at 25° C	1.13 – 1.15
Acid value, mg KOH/gm	23 – 27
Volatile content, %	35 – 39
Shelf life at 25° C, months	3
Gel time at 25° C, minutes*	10 – 20
Peak exotherm, °C**	170 – 180

* Mix VBR 2305PA Resin - 100 gml, VBR 1204 - 1.5ml

** Under insulated Condition for 100 gm mixture.

Caution : VBR 1201 should never be independently mixed with VBR 1204, as this would cause explosion.

PROPERTIES OF UNREINFORCED CURED RESIN CASTING

The specimens are prepared by separately mixing 1.5% ml of VBR 1204 with VBR 2305PA and casted in a closed cell of specified dimension. These castings are cured for 24 hrs at room temperature and post cured at 90°C for 4 hrs.



Vasavibala Resins (P) Ltd.

POLYMER DIVISION
Manufacturers of Unsaturated Polyester Resins

PROPERTIES OF RESIN CASTING

Barcol Hardness	40
Tensile Strength, MPa	45 - 50
Flexural Strength, MPa	75 - 85
Heat distortion temperature, °C	60 - 70
Water Absorption at 25°C over a period of 700 hrs, %	< 0.4
Elongation at break, %	>2

TEST METHOD

IS 6746 – 1994.

APPLICATION

VBR 2305PA reinforced with glass fiber gives laminates with excellent mechanical properties.

VBR 2305PA is specifically meant for the fabrication of small to large FRP articles where high production rates at room temperatures are required. This resin is well suited for use in thick sections. VBR 2305PA is suitable for wide range of applications in the chemical and transportation industries where both heat and weather resistances are prime criteria.

STORAGE

VBR 2305PA should be stored in closed containers inside covered area. The storage temperature not exceeding 25°C is preferable. At higher storage temperature, the shelf life decreases sharply. It should not be exposed to direct sunlight, heat radiation and moisture; these may cause premature gelation. VBR 2305PA is guaranteed for 3 months from the date of manufacture provided the storage conditions are strictly adhered to.

PACKING

35 Kg. HDPE carbuoys and 220 Kg. coated steel barrels.