



Vasavibala Resins (P) Ltd.

Regd. & Admin. Office : New No.44 (151) Eldams Road
Teynampet, Chennai-600 018.

Phone : 044-2435 8986 / 2435 2394 / 2435 2397

Factory : Shed No.64 SIDCO Industrial Estate,
Thirumazhisai, Chennai-600 124.

TECHNICAL DATA SHEET

PIGMENT RESIN - VBR-2308

Application	Saturated Polyester Resin for Pigment Dispersion
Chemical Nature	Orthophthalic
Appearance	Slightly Yellowish Clear Liquid
Colour (Max) Gardner Scale IS 6746:1994	1-3
Density @ 25°C, IS 6746:1994	1.18 – 1.22
Viscosity @ 25°C, cps IS 6746:1994	2000-2500
Acid Value, mg/KOH/gm IS 6746 :1994	24 – 28
Volatile content, % IS 6746 :1994	1 - 2